

# BC-400,BC-404,BC-408,BC-412,BC-416

## Premium Plastic Scintillators

The premium plastic scintillators described in this data sheet include those with the highest light output, as well as the most economical (BC-416). The chart below will direct you to the scintillator suitable for your energy application.

	BC-400	BC-404	BC-408	BC-412	BC-416
<b>Radiation Detected</b>					
<100keV X-rays			X		
100keV to 5MeV gamma rays				X	
>5MeV gamma rays	X				X
Fast neutrons				X	X
Alphas, betas		X	X		
Charged particles,cosmic rays, muons, protons, etc.			X	X	X
<b>Principal Uses/Applications</b>	general purpose	fast counting	TOF large area	large area	large area economy

### Scintillation Properties –

	BC-400	BC-404	BC-408	BC-412	BC-416
Light Output, %Anthracene	65	68	64	60	38
Rise Time, ns	0.9	0.7	0.9	1.0	–
Decay Time (ns)	2.4	1.8	2.1	3.3	4.0
Pulse Width, FWHM, ns	2.7	2.2	~2.5	4.2	5.3
Wavelength of Max. Emission, nm	423	408	425	434	434
Light Attenuation Length, cm*	160	140	210	210	210
Bulk Light Attenuation Length, cm	250	160	380	400	400

### Atomic Composition –

	BC-400	BC-404	BC-408	BC-412	BC-416
No. H Atoms per cc (x10 <sup>22</sup> )	5.23	5.21	5.23	5.23	5.25
No. C Atoms per cc (x10 <sup>22</sup> )	4.74	4.74	4.74	4.74	4.73
Ratio H:C Atoms	1.103	1.100	1.104	1.104	1.110
No. of Electrons per cc (x10 <sup>23</sup> )	3.37	3.37	3.37	3.37	3.37

\*The typical 1/e attenuation length of a 1x20x200cm cast sheet with edges polished as measured with a bialkali photomultiplier tube coupled to one end.

### General Technical Data –

Base .....	Polyvinyltoluene
Density (g/cc) .....	1.032 g/cc
Refractive Index .....	1.58
Expansion Coefficient (per°C,<67°C):	7.8X10 <sup>-5</sup>
Softening Point .....	70°C
Vapor Pressure .....	May be used in vacuum
Solubility .....	Soluble in aromatic solvents, chlorinated solvents, acetone, etc. Unaffected by water, dilute acids, lower alcohols, alkalis and pure silicone fluids or grease.
Light Output .....	At +60°C = 95% of that at +20°C. Independent of temperature from -60°C to +20°C



USA

Saint-Gobain Crystals  
17900 Great Lakes Parkway  
Hiram, OH 44234  
Tel: (440) 834-5600  
Fax: (440) 834-7680

Europe

Saint-Gobain Crystals  
104 Route de Larchant  
BP 521  
77794 Nemours Cedex, France  
Tel: 33 (1) 64 45 10 10  
Fax: 33 (1) 64 45 10 01

P.O. Box 3093  
3760 DB Soest  
The Netherlands  
Tel: 31 35 60 29 700  
Fax: 31 35 60 29 214

Japan

Saint-Gobain KK, Crystals Division  
3-7, Kojimachi, Chiyoda-ku,  
Tokyo 102-0083 Japan  
Tel: 81 (0) 3 3263 0559  
Fax: 81 (0) 3 5212 2196





China

Saint-Gobain (China) Investment Co., Ltd.  
15-01 CITIC Building  
19 Jianguomenwai Ave.  
Beijing 100004 China  
Tel: 86 (0) 10 6513 0311  
Fax: 86 (0) 10 6512 9843


www.detectors.saint-gobain.com

## BC-400, BC-404, BC-408, BC-412, BC-416 Premium Plastic Scintillators


### Emission Spectra



### Premium Plastic Scintillators Response to Atomic Particles



### Range of Atomic Particles in Premium Plastic Scintillators



Manufacturer reserves the right to alter specifications.  
©2005-8 Saint-Gobain Ceramics & Plastics, Inc. All rights reserved.